

**SYNKAD 202**  
**Boramide**  
**Corrosion Inhibitor**

**Synkad 202** is a water soluble, boramide corrosion inhibitor for use in synthetic and semi-synthetic metalworking fluids. **Synkad 202** inhibits rust on ferrous alloys without foaming or forming hard water soaps.

**Synkad 202** is formulated into water soluble synthetic and semi-synthetic metalworking fluids to provide corrosion protection to ferrous metals. In addition, the presence of boron in **Synkad 202** may aid in the inhibition of growth of bacteria. The following information represents typical starting point formulations guidelines:

	<u>% Weight</u>
Synthetic	3-10
Semi-Synthetic	5-20

**TYPICAL PROPERTIES**

Property	Result
Boron, %	4.4
Specific gravity @ 25°C	1.18
Density, lb/gal	9.9
pH Value, 1% in water	9.6
Viscosity @ 100°F, SUS (40°C, cSt)	6,300 (1,400)
Acid Value, mgKOH/g	Nil
Pour Point, °F (°C)	50 (10)
Color, ASTM	0.5
Base Value, mgKOH/g. eq.	520

**Synkad 202** should be stored in the original container or bulk storage tank at 60°-90°F. If frozen, it will reconstitute upon heating at 80°-100°F without mixing. Blending should not exceed 100°F.

The information contained on this data sheet is believed to be reliable. Since the conditions of application and use of our products are beyond our control, no warranty is expressed or implied regarding accuracy of the information, the results obtained from the use of the product, or that such use will not infringe on any patent. This information is furnished with the express condition that you will conduct your own tests to determine the suitability of the product for your particular use. (120412)

LGP-11®, LUBE-BOOSTER®, MAYCO®, PAROIL®, SUL-PERM®, SYN-CHEK®, SYNKAD®, CHLOREZ®, CHLOROWAX 40®, CHLOROWAX 50®, DOVERNOX®, DOVERPHOS®, DOVERPHOS HIPURE®, and DOVERPHOS S-9228® are federally registered trademarks of Dover Chemical Corporation.