

Product	% Total Ash (metal oxide)	% Free Fatty Acid	% Moisture	Melt Point, °C	Apparent Density (lb/ft ³)	% Passing thru #20 US Mesh	% Passing thru #100 US Mesh	% Passing thru #200 US Mesh	% Passing thru #325 US Mesh
Doverlube CA-20	11.4	1.0 max.	3.5 max.	152	41	95 min.	20 max.	-	-
Doverlube CA-21	11.4	1.0 max.	3.5 max.	152	15	-	-	95 min.	-
Doverlube CA-22	10.5 – 12.0	1.0 max.	3.5 max.	152	15	-	-	-	99 min.
Doverlube ZN-20	13.5	1.0 max.	0.5 max.	121	37	-	20 max.	-	-
Doverlube ZN-22	13.5	1.0 max.	0.5 max.	121	21	-	-	-	95 min.