



INVERSOL 140
Fatty Acid Ester
Inversely Soluble Lubricity Additive

Inversol 140 is a water soluble, complex ester based, lubricity additive designed for synthetic, water dilutable metalworking fluids. **Inversol 140** does NOT contain sulfur, phosphorus, or chlorine based components.

Inversol 140 is inversely soluble, forming an insoluble layer at elevated temperatures to impart a lubricating film at the tool/workpiece interface.

Inversol 140 works well with both ferrous and non-ferrous metals. Recommended treat rates are indicated below:

	<u>% Treat</u>
Synthetic metalworking fluid	3-10

Inversol 140 should be stored in an original container or bulk storage tank. Prolonged exposure to 0°F may result in solidification. Warming drums between 80-110°F should reverse solidification. Bulk storage should be maintained between 75-90°F with material being recirculated or mixed to avoid localized heating. Blending temperatures should not exceed 130°F.

TYPICAL PROPERTIES

Property	Result
Flash Point, C.O.C., °F (°C)	>350 (>177)
Specific Gravity @ 77°C	1.06
Density (lb/gal)	8.8
pH Value, 1% in water	7.1
Viscosity, SUS, @ 100°F (210°F)	7600 (600)
Viscosity, cSt, @ 40°C (100°C)	1,600 (125)
Acid Value (mgKOH/g)	15
Pour Point, °F (°C)	60 (16)
Color, ASTM	3.5
Inverse Solubility Temperature, °F (°C)	140 (60)

The information contained on this data sheet is believed to be reliable. Since the conditions of application and use of our products are beyond our control, no warranty is expressed or implied regarding accuracy of the information, the results obtained from the use of the product, or that such use will not infringe on any patent. This information is furnished with the express condition that you will conduct your own tests to determine the suitability of the product for your particular use. (111912)

LGP-11®, LUBE-BOOSTER®, MAYCO®, PAROIL®, SUL-PERM®, SYN-CHEK®, SYNKAD®, CHLOREZ®, CHLOROWAX 40®, CHLOROWAX 50®, DOVERNOX®, DOVERPHOS®, DOVERPHOS HIPURE®, and DOVERPHOS S-9228® are federally registered trademarks of Dover Chemical Corporation.