LARD OILS

Lubricity Additives

TYPICAL PROPERTIES

Designation	FAA as Oleic Acid	Color ASTM D1500	SAP #	Pour Point (°F)	Vis @ 100°F SUS	Flashpoint COC (°F)	Specific Gravity (60/60°F)
Prime Burning	0.5% max.	2.0 max.	195	45 max.	200	600 min.	0.915
Extra Winter Strained	4.0% max.	3.0 max.	195	45 max.	200	450 min.	0.915
No. 1	13 – 16%	3.5 - 6.0 max.	195	50 max.	195	430 min.	0.915

The information contained on this data sheet is believed to be reliable. Since the conditions of application and use of our products are beyond our control, no warranty is expressed or implied regarding accuracy of the information, the results obtained from the use of the product, or that such use will not infringe on any patent. This information is furnished with the express condition that you will conduct your own tests to determine the suitability of the product for your particular use. (112112)

LGP-11®, LUBE-BOOSTER®, MAYCO®, PAROIL®, SUL-PERM®, SYN-CHEK®, SYNKAD®, CHLOREZ®, CHLOROWAX 40®, CHLOROWAX 50®, DOVERNOX®, DOVERPHOS®, DOVERPHOS HIPURE®, and DOVERPHOS S-9228® are federally registered trademarks of Dover Chemical Corporation.

3676 Davis Road NW, Dover, OH 44622

330-343-7711 · 800-321-8805 · Facsimile 330-365-3926 · www.doverchem.com